

TASNEE PP H3030

POLYPROPYLENE

DESCRIPTION

TASNEE PP H3030 is a Polypropylene Homopolymer with a Melt Flow Rate (MFR) of 3.0 g/10min.

TASNEE PP H3030 is designed for use in Bi-axial Oriented Polypropylene (BOPP) film applications, offering excellent transparency and gloss, high stiffness and excellent processability. Its good mechanical properties and compliance to food contact regulations allow it to be used in various applications. Typical applications for BOPP film are: food packaging applications such as baked goods, pasta, snacks or confectionery and for non food packaging applications such as adhesive tapes, labels or print lamination.

TASNEE PP H3030 is formulated to be used in metalized film.

TASNEE PP H3030 is also a general purpose injection molding grade for technical items.

TYPICAL PROPERTIES

Physical	Method	Unit	Value
Melt Flow Rate (230°C/2.16 kg)	ISO 1133	g/10min	3.0
Melting Temperature	ISO 3146	°C	163
Vicat Softening Temperature	ISO 306	°C	154
Heat Distortion Temperature @ 455 KPa	ISO 75-2	°C	102
Density	ISO 1183	g/cm ³	0.9

Mechanical	Method	Unit	Value
Tensile Strength @ Yield	ISO 527-2	MPa	33
Tensile Elongation @ Yield	ISO 527-2	%	10
Flexural Modulus (1% Secant)	ISO 178	MPa	1450
Izod Impact Strength (Notched) at 23 °C	ISO 180-1A	J/m	32
Rockwell Hardness	ISO 2039-1	R	100

Typical Processing Conditions*

Extrusion Temperature	:	200 ~ 250°C
Chill Roll Temperature	:	20 ~ 40°C
MD Stretching Temperature	:	130 - 160°C
MD Stretching Ratio	:	4 ~ 7
TD Stretching Temperature	:	155 - 170°C
TD Stretching Ratio	:	7 ~ 10

* Processing parameters should only be used as guidelines.

FOOD CONTACT STATUS

TASNEE Polypropylene grade complies with recommendations and statutory regulations in the USA and European Union countries regarding packaging materials intended to come in contact with foodstuff. For more details, please, contact **TASNEE** below or our representative in your area.

SAFETY

The Material Safety Data Sheet (MSDS) contains information regarding health, safety and waste considerations for **TASNEE** Polypropylene grade. **TASNEE** urges each customer or recipient of MSDS to study it carefully to become aware of and understand the hazards associated with product. The customer should consider consulting reference works or individuals who are experts in ventilation, toxicology or fire prevention, as necessary or appropriate to use and understand the data contained in the MSDS.

STORAGE

Polypropylene material should be stored in a cool, dry place with adequate ventilation and absence of direct sunlight. Storage under improper conditions may initiate degradation process, adversely influencing processability, properties and visual aspect of transformed articles.

DISCLAIMER

"The information in this publication without prejudice, and is based on our current knowledge and experience and on a limited number of tests".

"In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication".

NATIONAL PETROCHEMICALS INDUSTRIALIZATION MARKETING COMPANY

P.O.Box: 26707

Riyadh 11496

Kingdom of Saudi Arabia

Tel: +966 1 473 4559

Fax: +966 1 473 4580

www.tasnee.com