

TALENE M2010 C01 Polypropylene Compound

DESCRIPTION

TALENE M2010 C01 is a 20% talc filled polypropylene homopolymer, with high flow, high stiffness, low odor, and high heat aging stability. The product is available in 102942 color version. It is used for heaters and air conditioning units.

It is not intended for medical, pharmaceutical and/or drinking water applications.

TYPICAL APPLICATIONS

Automotive components - heaters and air conditioning units

TYPICAL PROPERTIES

Physical	Method	Unit	Value
Density	ISO 1183	g/cm ³	1.04
Melt Flow Rate (230°C/2.16 kg)	ISO 1133	g/10min	10
Melt Volume Flow Rate (230°C/2.16 kg)	ISO 1133	g/10min	11.5
Mechanical	Method	Unit	Value
Tensile Modulus (Secant)	ISO 527-1, -2	MPa	2900
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	MPa	35
Tensile Strain at Yield (50 mm/min)	ISO 527-1, -2	%	5
Flexural Modulus (Secant)	ISO 178	MPa	3100
Flexural Stress (3.5 %)	ISO 178	MPa	50
Impact			
Charpy Unnotched Impact Strength (23°C, type 1, Edgewise)	ISO 179	kJ/m ²	40
Charpy Notched Impact Strength, (23°C, type 1, Edgewise, Notch A, complete break)	ISO 179	kJ/m ²	3.0
Hardness	Method	Unit	Value
Ball indentation hardness (H 358/30)	ISO 2039-1	MPa	95
Thermal	Method	Unit	Value
Vicat Softening Temperature, (B50 (50°C/h 50N))	ISO 306	°C	95
(B50 (50°C/h 10N))		°C	153
Heat deflection temperature A (1.80 MPa) Unannealed	ISO 75A-1, -2	°C	70

Notes:

Typical properties; not to be construed as specifications.

Safety

Workers should be protected from the possibility of skin or eye contact with molten polymer. As minimum precaution, safety glasses and heat resistance gloves are suggested to prevent mechanical or thermal injury to eyes and hands. Molten polymer exceeding processing condition requirements may degrade and release, fumes, vapors and unpleasant odor. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes and vapors. Legislation on the control of emissions and pollution prevention must be observed. If the principles of sound manufacturing practice are adhered to and the place of work is well ventilated, no health hazards are involved in processing the material.

The material may burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. In burning the material generates considerable heat and may release a dense black smoke. Fires should be extinguished by heavy foams or dry powder. For further information about safety in handling and processing please refer to the Safety Data Sheet (SDS).

Storage

The material is packed in 25 kg bags or in bulk containers protecting it from contamination. Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Keep material completely dry for good processing. Improper storage may bring damage to the packaging and can negatively affects on the quality of this product.

TASNEE will not give any warranty to unfavorable storage conditions which may lead to quality deterioration such as color change, bad smell and inferior product performance.

Disclaimer

"The information and data contained in this publication is submitted without prejudice, and is based on our current knowledge, experience and on a limited number of tests". "In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties nor of suitability for a specific purpose of the products made with or on the basis of the information in this publication".